Flexible Cementitious Waterproofing Membrane



PRODUCT DESCRIPTION

EDEN 2K is a dual component cementitious waterproofing membrane with embedded recent advances for flexible cementitious waterproofing membrane and is suitable for both positive and negative side waterproofing of interior and exterior concrete and masonry surfaces. The two component parts (Part A powder & Part B Liquid) on mixing yield a brush able, smooth slurry with excellent bond to most substrates. The product constituent ingredient is based on selected synthetic resins and cements.

SPECIAL FEATURES

- Suitable for use on below ground structures.
- Fast and easy to apply
- Excellent resistant to direct water penetration due to its hydrophobic nature.
- Provides anti-carbonation cover over concrete
- Superb adhesion properties.
- Can allow surface to breath (Permeable to water vapours) thus preventing build-up of moisture in structure, and reducing maintenance
- Elastomeric, thus provides excellent crack-bridging properties.
- Good bond/adhesion strength owing to its polymer modified properties.
- Good tolerance to domestic chemicals such as detergents.
- Features quick and easy installation.
- Does not support bacterial & Fungal growth and its Non-poisonous hence suitable for use in portable water tank applications.
- Can be applied by trowel, roller and airless spray machine.
- Can withstand moderate movement of hairline cracks. Bridges cracks up to 0.3mm in width, thank to its flexible nature and thus reducing maintenance.

WHERE TO USE

EDEN 2k is suitable for application in the following areas:

- ♣ Foundation wall Waterproofing
- ♣ Waterproofing of Retaining Walls and Basements
- Waterproofing Under-tile in Bathrooms, Terraces, and Roof gutters wet areas etc.
- Roofs slab and gutter Waterproofing
- Waterproofing of internal and external faces of water tanks, sumps, reservoirs, planter boxes etc., before tiling or other surface finishing.
- For use in the treatment of terraces, balconies,

- kitchen and toilet floors as a sandwich treatment, to prevent water ingress.
- Treating bridge and flyover decks before wearing course to protect concrete from rainwater ingress.

APPLICATION PROCEDURE

Stage-1: SURFACE PREPARATION & INVESTIGATIONS

A - Pre Substrate Investigation

- ♣ To further ensure durability and efficiency of membrane performance, substrate should possess a minimum compressive strength of at least 25MPa, and a cohesive bond strength of at least 1.5MPa.
- Check substrate for the presence of old loose coatings, dirt, fats, oils, organic substances, existing membranes and dust. In any case of the existence of the above listed, adequate surface preparatory measures should be employed such as surface grinding by means of a grinding machine.
- Ensure new concrete structures is cured for at least 28 days.
- All visible surface irregularities and indentations need to be smoothened and evened out using EDEN reprofiling range of mortars
- Ensure proper drainage to slope by means of an advance mortar modified screed using mortar modifiers such as EDEN mortar screed latex.

B - Surface Preparation

Careful surface preparation is essential for optimum finish and durability thus, surface needs to be clean, dry and sound, free of any contamination, which may harmfully affect the adhesion of the membrane. In order to achieve this, concrete surface must be mechanically profiled and prepared by shot blasting, sandblasting, water-jetting, scarifying, diamond-



AISE-OHIS EDEN CONSTRUCTION (CHEMICALS)

Flexible Cementitious Waterproofing Membrane

grinding or other engineering-approved method.

♣ The concrete or screed substrate has to be primed and/or levelled in order to achieve an even surface

C - Post Substrate Preparation Investigation

- Any uneven or visibly loose pieces needs to be chipped off and perfected using EDEN reprofiling range of mortars to achieved an excellent smooth finish.
- Thoroughly remove any evidence of grinding dust Observe.

Stage-2: APPLICATION A - Priming

EDEN 2K liquid can be used as a primer to prepared substrate for areas with minor hairline cracks prior to the normal product application process. This can be applied to prepared substrate by roller or brush in two coat and allowed to dry. Allow primer coat to cure for at least 1 – 3 hours or as observed (once tacky) and note that the curing rate may be affected by the prevailing weather condition and it is recommended that at least 2 layers priming are applied on areas where stronger protection is required. Best practice will suggest the use of Eden Latex as a substrate primer agent prior to product application. Please note that priming is optional and product application to SSD substrate will still be effective.

B - Mixing

EDEN 2K must be thoroughly mixed using a low speed electric stirrer (300- 400rpm) or other suitable equipment. Prior to mixing, stir part B mechanically after dispensing into a mixing container and when all of part A has been added to part B, mix continuously for 2 minutes minimum until a uniform homogenous mix has been achieved. Always ensure to follow the standard practice of pouring powder to liquid.

C - Application

Apply EDEN 2k to prepared substrate by roller, spraying equipment, trowel or brush. Ensure entire surface is uniformly coated leaving no puddle, air entrapments or undulation against the direction of screed bed slope when coating entire surface. Depending on application style adopted, where necessary, immediately roll in two directions with spiked roller to ensure even thickness and to remove entrapped air. Gradual spread over substrate



in order to minimize / avoid air entrapment is highly recommended. A minimum of two coat is recommended while taking note of faintly applied areas for immediate additional coating. It is extremely important that the area being treated is shaded from direct sun rays and wind to prevent rapid drying of the coating. Product should not be applied under active rain pour.

Trouble areas

Trouble areas such as wall- to-floor connections, 90° degree angles, chimneys, pipes/pipe openings, waterspouts (siphon), duct, drainage, etc should be reinforced using a fabric material. Apply EDEN 2K to the rightly sized fabric material to be used, ensuring it is fully saturated, then press in and dress the now soaked fabric material to the problem area.

Re-coat

Re-coat substrate once cured within 2-3 hours or once tacky.

C - Curing

EDEN 2K has good curing time but will experience accelerated curing under direct sunlight. Generally, It is important to protect EDEN 2K against rapid drying from exposure to direct sun ray, extreme temperatures or wind, hence curing by means of a curing compound or frequent water ponding/application is recommended.

RECOMMENDATION:

Before Use

It is recommended that product is stirred well before using for at least 2-3 min. Check product seal to ensure it is unbroken or fake. Consult customer support should any concern arise for clarity and Technical support.

General

- Generally, the use of a reinforcing fabric material is recommended for better membrane strength where necessary.
- Use 5-10cm stripe overlapping when using fibre material over very wide areas that would require joining.
- Re-coat After 2-3 hours, multiple layer coating gives strength to the membrane when finally cured.
- ♣ Apply multiple coat at demanding/troubled areas. A minimum of 3 coating is recommended.
- In a case where EDEN 2K is to be covered with ceramic tiles or similar material with similar application process, an additional waterproofed



Flexible Cementitious Waterproofing Membrane

mortar modified screed should be applied to membrane surface once cured to protect membrane from damage during tiling installation, However when dealing with an experienced tiler, tile adhesive



can be directly applied over membrane while taking care not to damage membrane during tile installation.

TECHNICAL PROPERTIES

Packaging	(A-20kg, & B-8kg) = 28kg pack	A-Powder & B-Liquid
Shelf life	12 months minimum from date of production	If stored properly inoriginal, unopened and undamaged sealed packaging.
Appearance	Part A - greyish, Part B - white liquid	Grey appearance when mixed.
Mix Ratio	Factory proportioned unit. (1 part liquid to 2.5 part powder can be adopted when mixing smaller quantities).	Mix entire contents.
Pot Life	Approximately 35-60minutes	Under normal conditions
Density (freshly mixed mortar)	~1.9 kg/L	(Part A+B mixed, +27 °C)
Tensile strength	>2N/mm2	ASTM D 412
Tensile adhesion strength	>2.4N/mm2	ASTM D 412
Adhesion to substrate	1.1N/mm2	ASTM D4541
Permeability to Water	Negligible (less than 0.1mm)	
Elongation at break	~60%	
Application Tolerance temp.	>+5°C	Minimum

APPLICATION INFORMATION

Cure Time Re-coat time	24 hrs minimum for initial curing Allow 2 - 3 hours minimum between coats	Dependent on application rate, effective sunlight accessed to the area and puddle concentrations.
Minimum Time To Re-coat	As Observed	Depending on application rate and style
Maximum Time To Re-coat	As Observed	Depending on application rate and style
Storage condition	Store in dry conditions in original packaging at temperatures between +5 °C and +30 °C.	Protect from direct sunlight and frost
Coverage	1.5 - 1.7kg / sqm coat for 1mm Dry film thickness in 2 coats.	Actual coverage depends upon the method of application, the texture and



Flexible Cementitious Waterproofing Membrane

COVERAGE ESTIMATION

The recommended coverage of Eden 2k is 1 kg/m² per coat to obtain an approximate wet film thickness of 0.8 mm (± 0.08mm) minimum.

Therefore, material requirement is approximately 2 kg/m^2 for a total dry film thickness (DFT) of 1 mm (\pm 0.1mm) in two coatings.

CAUSION

- Protect EDEN 2K membrane once cured from direct sunlight by using a suitable protection sheet or a cement screed or fibre cement board for floors.
- EDEN 2K is recommended for use only as described in the Uses section of this data sheet.
- Be careful to observe written instruction on all technical documents for this product such as Safety Data Sheet, Method Statement Data Sheet, Technical Data Sheet, and Test Certificate Results for Further details on Environmental Health and Safety.
- Application in cooler temperatures may require extra curing time before the installation of additionall coverings.
- **♣** Do not add water to dilute the material
- Coverage is changeable depending on the application type, surface porosity, surface profile, variation in level or wastage etc. it is recommended that at least 3 layers are applied.

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY HEALTH AND SAFETY

Information on the safe handling, storage and disposal of chemical products, user is advised to refer to the most recent/updated *Safety Data Sheet, Method Statement Data Sheet, and Technical Data Sheet,* containing physical, ecological, toxicological and other safety/handling/storage related data.

CLEAN UP

Wash hands and tools with EDEN super cleaner or any of EDEN recommended cleaning products promptly before the material hardens. Cured material must be mechanically removed.



TECHNICAL SUPPORT

AISE-OHIS *EDEN CONSTRUCTION (CHEMICAL) Ltd* provides a technical advisory service supported by a team of specialists in the field.

STORAGE AND SHELF LIFE

- EDEN 2K can be stored 12 months minimum from date of production if stored properly in original, unopened and undamaged / sealed packaging.
- EDEN 2K is supplied in a 20kg bag (powder) and a 8liter Keg (Liquid).
- Storage area should be free from direct sunlight rays.
- Storage area should be free from moisture and rain.
- Products should remain in their original, unopened containers, bearing the manufacturers name, product designation, and batch number and application precaution labels.

STANDARD COMPLIANCE

Conforms to EN 1489-2007, ASTM D-968

HEALTH & SAFETY

- Please ensure that hand gloves and goggles are worn during installation
- Apply in ventilated areas, away from flames
- It is only important that during application and after application, standard safety procedures are done.
- Please consult current MSDS for product.
- For Professional Use only.

ADDITIONAL INFORMATION

AISE-OHIS *EDEN CONSTRUCTION (CHEMICAL) Ltd* manufactures a complete range of construction chemical products which include:

- Cementitious Waterproofing membrane
- Acrylic Waterproofing membrane
- Polyurethane Waterproofing membrane
- **Bituminous Waterproofing membrane**
- Flooring solution
- Damp-Proofing products
- Repair and refurbishment systems
- ♣ Water-stop
- Cleaning agent



Technical Data Sheet

EDEN 2K

Flexible Cementitious Waterproofing Membrane

- Bonding agent
- ♣ Decorative / Repair mortars
- Tile adhesive ang grouts



For more information on any of our products, please contact AISE-OHIS *EDEN CONSTRUCTION (CHEMICAL)* global or regional office.

LEGAL NOTE

Details contained in this Technical Data Sheet is provided in good will based on the experience and knowledge of the products been stored, handled and applied properly under normal conditions. That client will be responsible to duly follow all instruction written herein. However, Whilst Aise-Ohis *Eden Construction (Chemicals)* Limited endeavors to ensure that any advice, recommendation, specification or information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it. Therefore, user is mandated to check/test product's suitability for the intended application and purpose. Aise-Ohis *Eden Construction (Chemicals)* Limited reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

